

L20 ANSWER 1 OF 1 CA COPYRIGHT 2009 ACS on STN
 AN 132:5633 CA
 ED Entered STN: 24 Dec 1999
 TI Producing portland cement from iron and steel slags and limestone
 AU Monshi, A.; Asgarani, M. K.
 CS Department of Materials, University of Technology, Esfahan, Iran
 SO Cement and Concrete Research (1999), 29(9), 1373-1377
 CODEN: CENRAI; ISSN: 0008-8846
 PB Elsevier Science Ltd.
 DT Journal
 LA English
 CC 58-1 (Cement, Concrete, and Related Building Materials)
 Section cross-reference(s): 60
 AB The slags from blast furnace (iron-making) and converter (steel-making), after magnetic separation, are mixed with limestone of six different compns. The ground materials are fired in a pilot plant scale rotary kiln to 1350 °C for 1 h. The clinker is cooled, crushed, mixed with 3% gypsum, and ground to fineness of more than 3300 cm²/g. Initial and final setting times, consistency of standard paste, soundness, free CaO, and compressive and fracture strengths after 3, 7, and 28 days are measured. Samples with higher lime saturation factor developed higher C₃S content and better mech. properties. Blending 10% extra iron slag to a cement composed of 49% iron slag, 43% calcined lime, and 8% steel slag kept the compressive strength of concrete above standard values for type I ordinary portland cement.
 ST portland cement manuf iron steel slag limestone raw material
 IT Slags
 (blast-furnace; producing portland cement from iron- and steel-making slags and limestone)
 IT Cement (construction material)
 (portland; producing portland cement from iron- and steel-making slags and limestone)
 IT Compressive strength
 Raw materials
 Recycling
 (producing portland cement from iron- and steel-making slags and limestone)
 IT Limestone, uses
 RL: NUU (Other use, unclassified); TEM (Technical or engineered material use); USES (Uses)
 (raw material; producing portland cement from iron- and steel-making slags and limestone)
 IT Slags
 (steelmaking, converter; producing portland cement from iron- and steel-making slags and limestone)
 IT 12168-85-3, c3s Cement component
 RL: TEM (Technical or engineered material use); USES (Uses)
 (content; producing portland cement from iron- and steel-making slags and limestone)
 RE.CNT 4 THERE ARE 4 CITED REFERENCES AVAILABLE FOR THIS RECORD
 RE
 (1) Komar, A; Building Materials and Components 1987, P136
 (2) Monshi, A; J Mater Sci 1991, V26, P3623 CA
 (3) Neville, A; Concrete Technology 1987, P8
 (4) Philipp, J; Utilisation of Blast Furnace and BOF Slag 1984, PA2